

LOCTITE



Loctite Repair eXtreme IDH 2146199

EAN code: 7332531013963

CHARACTERISTICS

- Water and solvent free repair adhesive based on FlexTec® technology
- High final strength and initial grip
- Flexible and vibration-resistant
- Gel texture
- Gap filling
- Safe and easy to use
- Solvent-free, no shrinkage
- 1-component, moisture-curing
- For interior and exterior application
- Water and ageing resistant.
- Not suitable for polypropylene polyethylene and Teflon®

APPLICATION FIELD

- For DIY, repair and modelling work in and around the house
- Glues many absorbent and non-absorbent materials like:
 - *Metals (aluminium, stainless steel, brass, steel, copper, zinc, etc.)
 - *Glass, concrete, ceramic, tiles, stone
 - *Wood, cork, paper, cardboard
 - *Textiles, leather, rubber, varnished surfaces.
 - *Plastics like rigid PVC, rigid polystyrene, polycarbonate, polymethylmethacrylat (PMMA, Plexiglas®), glass-fibre reinforced plastics such as reinforced polyester or polyamide, polystyrene foam (Styrofoam®).

Not suitable for polyethylene (PE), polypropylene (PP), polytetrafluoro-ethylene (PTFE) (Teflon®) and sensitive textiles.

INSTRUCTIONS FOR USE

Pretreatment

The material to be bonded should be clean and free of grease and dust. Clean laminates, metal etc. with solvent (washing benzene or alcohol). Additional abrading increases bonding strength with metals. The adhesive cures by absorbing moisture from the environment, so make sure the applied glue film has contact to ambient air. In case of gluing two non absorbent surfaces curing time can be slowed down. To optimize curing time you can previously clean surface with a damp cloth but make sure to avoid wetness, pooling water or drop formation.

For coated materials pretest adhesion and roughen if necessary

Application

Depending on the nature of your repair job you can choose among three different ways of applications:

1. Transparent bonding.

Apply **Loctite Repair eXtreme** in a thin layer to get a transparent film. Keep the items pressed for approx.1 hour.

2. Fill gaps.

Apply **Loctite Repair eXtreme** in a thick layer to fill gaps up to 5mm max. Fix or clamp the items together for 1 – 3 hours and do not touch or move them. In 24 hours, 70% of the full adhesion strength is achieved.

3. High initial grip.

Apply **Loctite Repair eXtreme** on both surfaces in thin and even layers. Leave for 3 minutes. Use as a contact adhesive. After **Loctite Repair eXtreme** become tacky, like pressure sensitive tape, bring the items together immediately and press firmly. Make sure the glue does not get a skin before assembling parts. Fixation is not necessary in many cases. Please note that final



Excellence is our Passion

strengths can decrease when used as contact glue.

By all applications, please make sure to keep the tube nozzle and cap clean and immediately tightly close cap to avoid curing of the glue at the nozzle.

TECHNICAL DATA

Composition	Flextec® polymer based
Density	ca. 1,1 g/cm ³ bei 25°C
Heat resistance	-50°C up to 120°C
Open time	3-5 min, depending on temperature and relative humidity
Application temperature	+5°C up to +40°C
Gap filling	Up to 5mm
Final lapshear strength (acc. DIN EN 205)	3-11 N/mm ² dep. on material
Shelf Life	18 months
Cure through speed	2mm every 24 hours, depending on temperature and humidity conditions

LIMITATIONS

Though adhesive is water resistant, no long term water immersion is recommendable.

Put the cap back immediately after applying the glue since it cures very fast.

Cleaning tools

Clean tools with thinner, alcohol or wash bencene immediately after use. Once cured **Loctite Repair eXtreme** is not soluble in any solvent and it can only be removed mechanically.

Storage

Store tightly close and at room temperature. Avoid humidity and temperatures lower +5°C and above +50°C.

HEALTH AND SAFETY

Before using the product please see related Material Safety Data Sheet that is available on request.



Excellence is our Passion

The information provided herein, especially recommendations for the use and application of our products, is based upon our current knowledge and experience. Due to different possible applications as well as varying application and working conditions, which are beyond our control, we strongly recommend to carry out sufficient extensive prior trials to confirm the suitability of our products for the relevant production processes, as well as the intended applications and results. Any liability in respect of the information in this Technical Data Sheet or any oral recommendations is excluded, except in the event of harm to life, physical injury or harm to health or if we are liable for gross negligence or willful misconduct or according to applicable mandatory product liability law.

Henkel Norden AB

Box 151 22, 167 15 Bromma.

Phone: +46 (0)10 480 7700

Internet: www.henkel.se